

Supplementary Material

Tab. S1 - P-values of mean colorimetric parameters of different techniques for wood from species of an Araucaria forest area. (+): significative at 95% confidence level.

Species	Mean all surfaces			Radial			Transversal		
	L*	a*	b*	L*	a*	b*	L*	a*	b*
<i>A. angustifolia</i>	0.02	0.02	0.00	0.18 ⁺	0.41 ⁺	0.00	0.01	0.00	0.00
<i>C. dinisii</i>	0.01	0.00	0.00	0.66 ⁺	0.02	0.00	0.00	0.00	0.00
<i>C. lilloi</i>	0.00	0.02	0.26 ⁺	0.10 ⁺	0.36 ⁺	0.63 ⁺	0.00	0.01	0.24 ⁺
<i>C. marginatum</i>	0.01	0.22 ⁺	0.00	0.00	0.38 ⁺	0.00	0.06 ⁺	0.01	0.04
<i>C. paniculata</i>	0.38 ⁺	0.04	0.00	0.78 ⁺	0.07 ⁺	0.00	0.37 ⁺	0.24 ⁺	0.00
<i>C. xanthocarpa</i>	0.62 ⁺	0.01	0.05	0.65 ⁺	0.18 ⁺	0.03	0.22 ⁺	0.01	0.21 ⁺
<i>M. coriacea</i>	0.00	0.05	0.00	0.13 ⁺	0.41 ⁺	0.00	0.00	0.01	0.00
<i>M. elaeagnoides</i>	0.10 ⁺	0.25 ⁺	0.44 ⁺	0.05	0.94 ⁺	0.57 ⁺	0.55 ⁺	0.11 ⁺	0.56 ⁺
<i>N. megapota mica</i>	0.00	0.53 ⁺	0.64 ⁺	0.05	0.37 ⁺	0.55 ⁺	0.00	0.06 ⁺	0.11 ⁺
<i>O. diospyrifolia</i>	0.02	0.12 ⁺	0.00	0.20 ⁺	0.58 ⁺	0.00	0.03	0.08 ⁺	0.00
<i>P. lambertii</i>	0.01	0.56 ⁺	0.00	0.00	0.55 ⁺	0.00	0.11 ⁺	0.11 ⁺	0.17 ⁺
<i>P. peruviana</i>	0.00	0.02	0.63 ⁺	0.00	0.37 ⁺	0.02	0.00	0.01	0.01
<i>Z. rhoifolium</i>	0.61 ⁺	0.29 ⁺	0.04	0.06 ⁺	0.49 ⁺	0.09 ⁺	0.42 ⁺	0.01	0.19 ⁺

Tab. S2 - Color classification for species by each method. (*): Classification in an approximate group.

Species	Colorimetry	Spectrophotometry
<i>A. angustifolia</i>	Pinkish gray	Pinkish gray
<i>C. dinisii</i>	Pinkish gray	Pinkish gray
<i>C. lilloi</i>	Brownish yellow	Brownish yellow
<i>C. marginatum</i>	Grayish pink	Yellowish olive
<i>C. paniculata</i>	Light olive*	Grayish white*
<i>C. xanthocarpa</i>	Grayish pink	Grayish pink
<i>M. coriacea</i>	Pinkish gray	Pinkish gray
<i>M. elaeagnoides</i>	Grayish pink	Grayish pink
<i>N. megapotamica</i>	Pinkish gray*	Pinkish gray*
<i>O. diospyrifolia</i>	Pinkish gray*	Yellowish olive
<i>P. lambertii</i>	White	White
<i>P. peruviana</i>	Grayish pink	Olive
<i>Z. rhoifolium</i>	Light olive*	Light olive*

Fig. S1 - Mean colorimetric parameters from radial (R) and transversal (X) surface of wood from species from an Araucaria forest area. Bars indicate upper standard deviation.




Fig. S2 - Principal component analysis score graph with average radial surface data for colorimetric parameters of wood from Araucaria forest species.




Fig. S3 - Principal component analysis score graph with average transversal surface data for colorimetric parameters of wood from Araucaria forest species.

